



# Technical Data Sheet

Product Name  
**SCGC™ HDPE**

Product Type  
**High Density Polyethylene**

Product Grade  
**H6140B**

## Product Description

SCGC HDPE H6140B is a high density polyethylene resin suitable for producing cosmetic bottles by using extrusion blow molding machine.

## Typical Application

- Personal and homecare bottles
- Lube oil bottles
- Brake fluid bottles
- Chemical bottles
- Milk bottles

## Product Characteristics

- Excellent surface appearance
- Good impact and compressive strength
- Good processability
- Good printability

## International Compliance

- U.S FDA 21 CFR 177.1520
- Regulation (EU) No.10/2011
- Packaging and Packaging waste directive 94/62/EC/CONEG

## Physical Properties

| Properties                | Test Method   | Typical Value | Unit                 |
|---------------------------|---|---------------|----------------------|
| Melt Flow Rate            | ASTM D 1238 @ 190 °C, 2.16 kg                                     | 0.3           | g/ 10 min            |
| Density                   | ASTM D 1505   | 0.960         | g/cm <sup>3</sup>    |
| Melting Point             | ASTM D 2117   | 132           | °C                   |
| Vicat Softening Point     | ASTM D 1525   | 128           | °C                   |
| Brittleness Temperature   | ASTM D 746  | < - 60        | °C                   |
| Tensile Strength at Yield | ASTM D 638  | 300           | kg/cm <sup>2</sup>   |
| Tensile Strength at Break | ASTM D 638  | 330           | kg/cm <sup>2</sup>   |
| Elongation at Break       | ASTM D 638  | 1100          | %                    |
| Flexural Modulus          | ASTM D 790  | 14500         | kg/cm <sup>2</sup>   |
| Notched Izod Impact       | ASTM D 256 @ 23 °C  | 98            | J/m                  |
| ESCR                      | ASTM D 1693 @ 50 °C<br>(Method B, Compression Molded, 25% Igepal) | 100           | Hrs, F <sub>50</sub> |

**Note:** The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.



|  |                                   |
|--|-----------------------------------|
| <b>Technical Data Sheet</b>                      | Product Name<br><b>SCGC™ HDPE</b> |
| Product Type<br><b>High Density Polyethylene</b> | Product Grade<br><b>H6140B</b>    |

## Processing Guidelines

Recommended processing conditions:

The actual extrusion condition depends on type of using machine, size and wall thickness of product required. Generally, melt temperature should be 160-180 °C. 5-8 bar of blowing pressure is recommended. In some cases, enlargement of die and pin diameter (15-30%) may be suggested for increasing parison diameter.

## Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

## Product Available Form

- Block pellet

## Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

## Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be sloped.

## Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services.



|  |                                   |
|--|-----------------------------------|
| <b>Technical Data Sheet</b>                      | Product Name<br><b>SCGC™ HDPE</b> |
| Product Type<br><b>High Density Polyethylene</b> | Product Grade<br><b>H6140B</b>    |

## Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

## Related Documents

- The latest version of this document will be available at our website, [www.scgchemicals.com](http://www.scgchemicals.com), or can be obtained from the SCG Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Safety Data Sheet.
  - Declaration of compliance.

## Disclaimer

- The applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.