

Technical Data Sheet

Product Name

SCGCTM PVC

Product Type

PVC Resin - Non Bis-A Grade

Product Grade SP66J

Product Description

SCGC PVC SP66J is polyvinyl chloride homopolymer having medium molecular weight, SP66J is white and free-flowing resins produced by suspension polymerization process. The resin can easily blend with variety of additives to achieve desired qualities needed in many applications. Applications are ranging from general purpose to special products regarding customer's satisfactions.

Typical Application

 Rigid pipe, door and window frames, edge band, conduit, other rigid profiles

Product Characteristics

- Good thermal stability
- · Good electrical resistance

International Compliance

- Food contact applicable* (US FDA CFR 175.300)
- Not contained of specified substances according to RoHS, EU
- REACH compliance, EU
- Bisphenol-A Free

Physical Properties

Properties	Test Method	Typical Value	Unit
K-Value	ISO 1628-2	66.0*	-
Appearent Bulk Density	ISO 60	0.56	g/ml
Volatile Matter	ISO 1269	< 0.3	%
Sieve Analysis	ASTM D 1921		kg/cm²
 Retained on 250 micron 		< 2	%
 Retained on 75 micron 		> 90	%
Impurity and Foreign Matter	ISO R 1265	< 10	points/100squares
Residual VCM	ASTM D 3749	<1	ppm

Note: *Corresponding Polymerization Degree = 1000

^{*}this will legally not exempt the producers of final Food contact articles ot perform testing on their own products.



Technical Data Sheet

Product Name

SCGCTM PVC

Product Type

PVC Resin - Non Bis-A Grade

Product Grade SP66J

Processing Guidelines

PVC resin needs to be compounded with the properly additives by using standard mixing techniques. The optimum processing condition for each convertor depends on the formulation and the machine. Generally, the processing temperature is $120 \text{ to } 170^{\circ}\text{C}$ for soft products and $170 \text{ to } 210^{\circ}\text{C}$ for rigid products.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

· White powder

Product Packaging

- Paper bag 25 kilograms
- Flexy bag 550 and 1,100 kilograms
- Tank car 10 and 20 metric tons
- Sea bulk 17 metric tons

Storage

- Use with adequate ventilation. Avoid contact with eyes and skin. Good housekeeping measures should be used and accumulations of materials should be removed from settling areas.
- Polyvinyl Chloride can acquire a substantial static electrical charge. Handling and processing equipment should have an electrical grounding.
- Store and handle in accordance with all current regulations and standards. Container tightly closed and properly labeled. Store in a cool, dry area. Store in a well-ventilated area. Avoid heat, flames, sparks and other sources of ignition.
- Recommend to use the product within 1 year, start from manufacturing period which is referenced from lot number printed on package, to prevent any changing.
- · Arrange product properly and correctly methods. For more information, please see "PVC User manual"

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services.



Technical Data Sheet

Product Name

SCGCTM PVC

Product Grade

SP66J

Product Type

PVC Resin - Non Bis-A Grade

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Safety Data Sheet
 - PVC User Manual

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials