



# Technical Data Sheet

Product Name  
**SCGC™ HDPE**

Product Type  
**High Density Polyethylene**

Product Grade  
**H6105JU**

## Product Description

SCGC™ HDPE H6105JU is high stiffness and balanced impact property of high density polyethylene resin. This grade is added UV resistance suitable for industrial product produced from injection molding process.

## Typical Application

- Large container, garbage bin, Fruit basket
- Pallet, Crate
- Industrial parts
- Outdoor application

## Product Characteristics

- Good stiffness, impact resistance
- Good processibility
- UV resistance

## International Compliance

- Directive 94/62/EC (Packaging and Packing waste)
- RoHS Directive 2011/65/EU (RoHS)
- REACH Regulation (EC) No.1907/2006

## Physical Properties

| Properties                        | Test Method                            | Typical Value | Unit               |
|-----------------------------------|--|---------------|--------------------|
| Melt Flow Rate                    | ASTM D 1238 @ 190 °C, 2.16 kg          | 5             | g/10 min           |
| Density                           | ASTM D 1505                            | 0.964         | g/cm <sup>3</sup>  |
| Melting Point                     | ASTM D 2117                            | 133           | °C                 |
| Vicat Softening Point             | ASTM D 1525                            | 127           | °C                 |
| Heat Deflection Temperature (HDT) | ASTM D 648 @ 4.6 kg/cm <sup>2</sup>    | 75            | °C                 |
| Tensile Strength at Yield         | ASTM D 638                             | 250           | kg/cm <sup>2</sup> |
| Tensile Strength at Break         | ASTM D 638                             | 200           | kg/cm <sup>2</sup> |
| Flexural Modulus                  | ASTM D 790                             | 15,500        | kg/cm <sup>2</sup> |
| Notched Izod Impact               | ASTM D 256 @ 23°C                      | 32            | J/m                |
| Hardness                          | ASTM D 2240                            | 66            | Shore D            |
| Flexural Modulus                  | ASTM D 790 (Injection specimen)        | 10,400        | kg/cm <sup>2</sup> |
| Notched Izod Impact               | ASTM D 256 @ 23°C (Injection specimen) | 72            | J/m                |

### Note:

- Conversion factor for changing unit from kg/cm<sup>2</sup> to MPa is divided by 10.20
- The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.



|  |                                   |
|--|-----------------------------------|
| <b>Technical Data Sheet</b>                      | Product Name<br><b>SCGC™ HDPE</b> |
| Product Type<br><b>High Density Polyethylene</b> | Product Grade<br><b>H6105JU</b>   |

## Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 200-250 °C      Mold temperature: 20-60 °C      Injection speed: Fast      Screw speed 40-70 rpm  
Pressure: Injection 30-70%,      Packing and Holding 30-50%,      Back 10% of Max. Pressure

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical services at the address as specified below.

## Product Available Form

- Pellet

## Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

## Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

## Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services



|  |                                   |
|--|-----------------------------------|
| <b>Technical Data Sheet</b>                      | Product Name<br><b>SCGC™ HDPE</b> |
| Product Type<br><b>High Density Polyethylene</b> | Product Grade<br><b>H6105JU</b>   |

## Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

## Related Documents

- The latest version of this document will be available at our website, [www.scgchemicals.com](http://www.scgchemicals.com), or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Safety Data Sheet
  - Declaration of Compliance.

## Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials