

Product Description

ICORENE® 1314 is high performance hexene linear medium density polyethylene specifically developed for use in rotational moulding.

ICORENE® 1314 is designed for use in many different rotomoulding applications. It has been designed for applications requiring good stiffness and toughness. It can be used for Food Contact applications.

Typical Applications

- Large tanks
- Fuel oil tanks
- Septic tanks

Product Characteristics

- Good impact strength
- Good stiffness

Physical Properties

Property	Test Method	Typical Values	Unit
Resin Properties			
Melt Flow Rate	ASTM D 1238 @ 190°C, 2.16 kg	3.0	g/10 min
Density	ASTM D 1505 (anneal)	0.939	g/cm ³
Heat Deflection Temperature, 0.45 MPa	ASTM D 648	67 (153)	°C (°F)
Mechanical Properties			
Tensile Strength-at-Yield	ASTM D 638	20 (2900)	MPa (Psi)
Elongation-at-Break	ASTM D 638	>1000	%
Flexural Modulus	ASTM D 790	800 (116000)	MPa (Psi)
Surface Hardness	ASTM D 2240	62	Shore D
Dart Impact Strength @ -20 °C	Internal test (based on ISO 6603)	>20	J/mm
Charpy Impact Strength @ 23 °C	ISO 178 / 1ea	13	kJ/m ²
ESCR @ 50°C, 100% IGEPAL	ASTM D 1693	>1000	Hrs

Note: the given values are average values for the base resin and should not be used for specification limits.

Processing Guidelines

Moulding cycles depend on mould materials and its wall thickness, oven temperature, and shot size. Typical oven temperatures should be set between 250 and 300 °C.

Points of Concerns

Finishing rotational part by flaming can decrease mechanical properties of rotational parts, which is not recommended.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, please contact your SCG ICO Polymers / SCG Performance Chemicals technical service at the address or telephone number as specified below.

Product Available Forms

- Natural powder
- Color powder

Product Packaging

- 20 kg loose bag

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG ICO Polymers technical service.

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG ICO Polymers technical service.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG ICO Polymers technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Material Safety Datasheet
 - Statement on compliance to food contact regulations

Disclaimer

- The product can be used only for the application as specified here above.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.
- We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.
- No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.