



Technical Data Sheet

Product Name
SCGC HDPE

Product Type
PE100 Black HDPE Compound for Injection Molding

Product Grade
H1000PCI

Product Description

SCGC HDPE H1000PCI is a black, bimodal technology, high density polyethylene compound classified as MRS 10.0 material (PE100) providing superior mechanical properties and processability. In addition, it includes a good dispersion of carbon black pigment and anti-oxidant to ensure excellent long term UV resistance and thermal stability.

Typical Application

- Injection molding fitting element for butt-fusion and electrofusion socket and saddle welding pipes

Product Characteristics

- High productivity
- Easy flow and less energy consumption
- High thermal stability

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate	ISO 1133 @ 190 °C, 5.0 kg	0.40	g/ 10 min
Density (Compound)	ISO 1183	0.960	g/cm ³
Tensile Strength at Yield	ISO 527 @ Crosshead speed 100 mm/ min	24	MPa
Tensile Strength at Break	ISO 527 @ Crosshead speed 100 mm/ min	> 30	MPa
Elongation at Break	ISO 527 @ Crosshead speed 100 mm/ min	> 600	%
Carbon Black Content	ISO 6964	2.25	% by mass
Carbon Black Dispersion	ISO 18553	< 3	-
Oxidative Induction Time	ISO 11357-6 @ 210 °C	≥ 40	Min
Flexural Modulus	ASTM D790	950	MPa
Melting Temperature	ASTM D 2117	130	°C
Heat Deflection Temperature	ASTM D 648 (4.6 kg/cm ³)	80	°C
Vicat Softening Point	ASTM D 1525	124	°C
MRS Classification	ISO 12162/ISO 9080	10.0	MPa
Resistance to Slow Crack Growth	ISO 13479 @ 80 °C	> 500	Hrs

- Note:**
- The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
 - Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20.



Technical Data Sheet

Product Name

SCGC HDPE

Product Type

PE100 Black HDPE Compound for Injection Molding

Product Grade

H1000PCI

Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommend processing condition: Drying temperature at 80 °C for 5 hours, Melt temperature 180 – 250 °C, Medium injection speed, Screw speed 60 – 100 rpm, Mold or cooling temperature 50 – 70 °C

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- Black Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical service.



Technical Data Sheet

Product Name

SCGC HDPE

Product Type

PE100 Black HDPE Compound for Injection Molding

Product Grade

H1000PCI

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical service.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Material Safety Data Sheet
 - Statement on compliance to food contact regulation.

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials