



TECHNICAL DATA SHEET

Product Name

SCG PVC

Product Type

PVC Resin - High K-Value Grade

Product Grade

SG730

Product Description

Polyvinyl Chloride Homopolymer having high molecular weight, is white and free-flowing resins produced by suspension polymerization process. The resin can easily blend with variety of additives to achieve desired qualities properties e.g. high strength, needed in many applications. The high K value PVC resin is developed to serve the application which high mechanical properties e.g. high strength, strength, high pressure are needed.

Typical Application

- Flexible & transparent sheet (packaging, stationery, etc.)
- High strength flexible sheet (matt cover, etc.)
- Flexible profile, high strength & abrasion resistance flexible product (automotive parts, hose, etc.)
- High strength and thermal stability wire & cable, wire harness
- Flexible product (automotive

Product Characteristics

- Excellent Plasticizer Absorption and Dry-Up Abilities
- Excellent Electrical Properties
- Excellent Mechanical Performance of Finished Products

International Compliance

- REACH Compliance, EU
- Food Contact Applicable* (US FDA CFR177.1975, US)
- Not Contained of Specified Substances according to RoHS, EU

* This will legally not exempt the producers of final Food Contact articles to perform testing on their own products.

Physical Properties

Property	Test Method	Typical Value	Unit
K-Value	ISO - 1628-2	73*	-
Apparent Bulk Density	ISO - 60	0.48	g/ml
Volatile Matter	ISO - 1269	< 0.3	%
Sieve Analysis	ASTMD - 1921		
• Retained on 250 micron		0	%
• Retained on 75 micron		> 90	%
Impurity and Foreign Matter	ISO/R - 1265	< 5	Specks/100sq.
Residual VCM	ASTM D -3749	< 1	ppm

* Corresponding Polymerization Degree = 1400



TECHNICAL DATA SHEET

Product Name

SCG PVC

Product Type

PVC Resin - High K-Value Grade

Product Grade

SG730

Processing Guidelines

PVC resin needs to be compounded with the properly additives by using standard mixing techniques. The optimum processing condition for each convertor depends on the formulation and the machine. Generally, the processing temperature is 120 to 170 °C for soft products and 170 to 210 °C for rigid products.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- White powder

Product Packaging

- Paper Bag 25 kilograms
- Flexy Bag 600 and 1,100 Kilograms
- Tank Car 12, 16.5, and 27 Metric Tons
- Seabulk 18 Metric Tons

Storage

- Use with adequate ventilation. Avoid contact with eyes and skin. Good housekeeping measures should be used and accumulations of materials should be removed from settling areas.
- Polyvinyl Chloride can acquire a substantial static electrical charge. Handling and processing equipment should have an electrical grounding.
- Store and handle in accordance with all current regulations and standards. Container tightly closed and properly labeled. Store in a cool, dry area. Store in a well-ventilated area. Avoid heat, flames, sparks and other sources of ignition.
- Arrange product properly and correctly methods. For more information, please see "PVC User manual"

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.



TECHNICAL DATA SHEET

Product Name

SCG PVC

Product Type

PVC Resin - High K-Value Grade

Product Grade

SG730

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

Related

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Plastics/SCG Performance Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Material Safety Datasheet
 - PVC User Manual

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.