



# TECHNICAL DATA SHEET

Product Name

**SCG PVC**

Product Type

**PVC Resin - Medical Grade**

Product Grade

**SM58S**

## Product Description

Polyvinyl Chloride Homopolymer having low molecular weight, is white and free-flowing resins produced by suspension polymerization process. The resin can easily blend with variety of additives to achieve desired qualities needed in many applications. The medical grade PVC resin is developed for medicals application which more concerned about health safety.

## Typical Application

- Medical rigid & semi rigid sheet
- Medical devices (connector, wing, cap, chamber, etc.)

## Product Characteristics

- Excellent Thermal Stability

## International Compliance

- REACH Compliance, EU
- Biological Testing, Japan

## Physical Properties

Property	Test Method	Typical Value	Unit
K-value	ISO- 1628-2	58*	-
Apparent Bulk Density	ISO-60	0.56	g/ml
Volatile Matter	ISO-1269	<0.3	%
Sieve Analysis	ASTM-1921		
- Retained on 250 micron		0	%
- Retained on 75 micron		>90	%
Impurity and Foreign Matter	ISO/R-1265	<5	Specks/100sq
Residual VCM	ASTM D3749	<1	ppm
Fish Eye	TPC Method	<5	Point/150 cm <sup>2</sup>
Elution Test	TPC Method	Passed	-

\*Corresponding Polymerization Degree = 700



## TECHNICAL DATA SHEET

Product Name

**SCG PVC**

Product Type

**PVC Resin - Medical Grade**

Product Grade

**SM58S**

### Processing Guidelines

PVC resin needs to be compounded with the properly additives by using standard mixing techniques. The optimum processing condition for each convertor depends on the formulation and the machine. Generally, the processing temperature is 120 to 170 °C for soft products and 170 to 210 °C for rigid products.

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

### Product Available Form

- White powder

### Product Packaging

- Paper Bag 25 kilograms
- Flexy Bag 550 and 1,100 Kilograms
- Tank Car 10 and 20 Metric Tons
- Seabulk 17 Metric Tons

### Storage

- Use with adequate ventilation. Avoid contact with eyes and skin. Good housekeeping measures should be used and accumulations of materials should be removed from settling areas.
- Polyvinyl Chloride can acquire a substantial static electrical charge. Handling and processing equipment should have an electrical grounding.
- Store and handle in accordance with all current regulations and standards. Container tightly closed and properly labeled. Store in a cool, dry area. Store in a well-ventilated area. Avoid heat, flames, sparks and other sources of ignition.
- Arrange product properly and correctly methods. For more information, please see "PVC User manual"

### Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.



## TECHNICAL DATA SHEET

Product Name

**SCG PVC**

Product Type

**PVC Resin - Medical Grade**

Product Grade

**SM58S**

### Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

### Related

- The latest version of this document will be available at our website, [www.scgchemicals.com](http://www.scgchemicals.com), or can be obtained from the SCG Plastics/SCG Performance Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Material Safety Datasheet
  - PVC User Manual

### Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.