



TECHNICAL DATA SHEET

Product Name

SCG PP

Product Type

High Density Polyethylene for Caps and Closures

Product Grade

P443J

Product Description

SCG PP P443J is an impact copolymer polypropylene resin with good processability and good mechanical properties. It is particularly designed for injection molding and continuous compression molding of beverage caps and closures.

Typical Application

- Beverage caps and closures
- Carbonated soft drink
 - Hot-filled beverage

Product Characteristics

- Excellent processability
- High stiffness
- High heat resistance
- With Slip agent for good removal torque

International Compliance

- US FDA 21 CFR 177.1520
- Regulation (EU) No. 10/2011

Note: Direct food contact is subjected to the extraction provisions of the regulation on the finished food contact package.

Typical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate (190°C, 2.16 kg)	ASTM D1238	6.0	g/10 min
Density	ASTM D1505	0.910	g/cm ³
Tensile Strength at Yield	ASTM D638	290	kg/cm ²
Tensile Strength at Break	ASTM D638	200	kg/cm ²
Elongation at Break	ASTM D638	130	%
Flexural Modulus	ASTM D790	15,000	kg/cm ²
Notched Izod Impact Strength (at 0°C)	ASTM D256	78	J/m
Notched Izod Impact Strength (at 23°C)	ASTM D256	108	J/m
Melting Point	ASTM D2117	165	°C
Heat Deflection Temperature at 4.6 kg/ cm ²	ASTM D648	120	°C

Note: The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.



TECHNICAL DATA SHEET

Product Name

SCG PP

Product Type

High Density Polyethylene for Caps and Closures

Product Grade

P443J

Processing Guidelines

The actual processing condition depends on each machine type, product size and mold design. Generally, melt temperature should be 190-230°C for injection molding and 160-190°C for continuous compression molding. The exceed melt temperature than 250°C might affect organoleptic property

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service by email or the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabeled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your technical service.



TECHNICAL DATA SHEET

Product Name

SCG PP

Product Type

High Density Polyethylene for Caps and Closures

Product Grade

P443J

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your technical service.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Material Safety Datasheet
 - Statement on compliance to food contact regulations

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.