



# TECHNICAL DATA SHEET

Product Name

**SCG HDPE**

Product Type

**High Density Polyethylene for Blow Molding**

Product Grade

**H6140B**

## Product Description

SCG HDPE H6140B is a high density polyethylene resin suitable for producing cosmetic bottles by using extrusion blow molding machine

## Typical Application

- Personal and homecare bottles
- Lube oil bottles
- Brake fluid bottles
- Chemical bottles
- Milk bottles

## Product Characteristics

- Excellent surface appearance
- Good impact and compressive strength
- Good processability
- Good printability

## International Compliance

- U.S FDA 21 CFR 177.1520
- Regulation (EU) No.10/2011
- Packaging and Packaging waste Directive 94/62/EC/CONEG

## Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 190 °C, 2.16 kg	0.3	g/10 min
Density	ASTM D 1505	0.960	g/cm <sup>3</sup>
Melting Point	ASTM D 2117	132	°C
Vicat Softening Point	ASTM D 1525	128	°C
Brittleness Temperature	ASTM D 746	< - 60	°C
Tensile Strength at Yield	ASTM D 638	300	kg/cm <sup>2</sup>
Tensile Strength at Break	ASTM D 638	330	kg/cm <sup>2</sup>
Elongation at Break	ASTM D 638	1100	%
Flexural Modulus	ASTM D 790	13000	kg/cm <sup>2</sup>
Notched Izod Impact	ASTM D 256 @ 23 °C	98	J/m
ESCR	ASTM D 1693 @ 50 °C (Condition B, Compression Molded, 25% Igepal)	100	Hrs, F50

**Note:** the given values are typical value measured on the product. Values herein are not to be constructed as a product specification.



## TECHNICAL DATA SHEET

Product Type

**High Density Polyethylene for Blow Molding**

Product Name

**SCG HDPE**

Product Grade

**H6140B**

### Processing Guidelines

Recommended processing conditions:

The actual extrusion condition depends on type of using machine, size and wall thickness of product required. Generally, melt temperature should be 160-180 °C. 5-8 bar of blowing pressure is recommended. In some cases, enlargement of die and pin diameter (15-30%) may be suggested for increasing parison diameter.

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service engineer at the address or telephone number as specified below.

### Product Available Form

- Block pellet

### Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container

### Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabeled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be sloped.

### Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your technical service.



## TECHNICAL DATA SHEET

Product Type

**High Density Polyethylene for Blow Molding**

Product Name

**SCG HDPE**

Product Grade

**H6140B**

### Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your technical service.

### Related Documents

- The latest version of this document will be available at our website, [www.scgchemicals.com](http://www.scgchemicals.com), or can be obtained from the technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Material Safety Datasheet
  - Statement on compliance to food contact regulations

### Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.