



Technical Data Sheet

Product Type

Polyethylene for Rotational MouldingProduct Name
SCGC™ LLDPEProduct Grade
M20

Product Description

SCGC™ LLDPE M20 series is color compound linear-low density polyethylene (LLDPE) for rotational moulding applications. This grade is suitable for rotational moulding of storage tanks and general-purpose applications which are indoor / semi-indoor or for thin wall (less than 5 mm) parts.

Typical Application

- Water storage tanks
- Small to medium tanks (< 5,000 L)¹
- Material handling equipment

Product Characteristics

- High stiffness
- Good impact strength
- Fast cooking
- UV-stabilized (UV2) for indoor / semi-indoor

International Compliance

- Base resin meets the requirements of U.S. Food and Drug Administration (FDA) 21 CFR Part 177.1520 Olefin polymers (c) 2.1 for food contact under conditions of use D-G (21 CFR 176.170(c) Table 2)

¹ Depending of tank thickness which is designed by height, diameter and specific gravity of fluid.

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate @ 190°C, 2.16 kg	ASTM D 1238	4.0	g/10 min
Density	ASTM D 1505	0.938	g/cm ³
Melting Point	ASTM D 2117	125 (257)	°C (°F)
Crystallization Point	ASTM D 2117	113 (236)	°C (°F)
Heat Deflection Temperature	ASTM D 648 @ 0.455 MPa	65 (149)	°C (°F)
Vicat Softening Temperature	ASTM D 1525	116 (241)	°C (°F)
Mechanical Properties			
Tensile Strength at Yield @ Speed 50 mm/min	ASTM D 638	20 (2900)	MPa (psi)
Tensile Strength at Break @ Speed 50 mm/min	ASTM D 638	18 (2600)	MPa (psi)
Elongation at Break @ Speed 50 mm/min	ASTM D 638	800	%
Flexural Modulus	ASTM D 790	700 (102000)	MPa (psi)
Surface Hardness	ASTM D 2240	60	Shore D
ARM Impact Strength @ -40°C (5.5 mm rotomolded sample)	ARM Method	27 (110)	J/mm (lb·ft)
Brittleness Temperature	ASTM D 746	< -60 (-76)	°C (°F)

Note: • The given values are typical value measured on the product. Values herein are not to be construed as a product specification.



Technical Data Sheet

Product Type

Polyethylene for Rotational Moulding

Product Name
SCGC™ LLDPE

Product Grade
M20

Processing Guidelines

Moulding cycles depend on mould materials and its wall thickness, oven temperature, and shot size. Typical oven temperatures should be set between 250 and 300 °C. The recommended PIAT for M20 color compound is about 180 °C but may vary with a color shade.

Points of Concerns

- It is not recommended to flame the surfaces of molded parts with an open torch due to risk of thermal degradation and premature failure.
- M20 is not recommended for parts which exceed 5 mm or 30 min heating.
- M20 is not recommended for products used under direct and intense sunlight.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Pellet
- Color compound powder

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services.



Technical Data Sheet

Product Type

Polyethylene for Rotational Moulding

Product Name
SCGC™ LLDPE

Product Grade
M20

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Safety Data Sheet
 - Declaration of Compliance

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.