Technical Data Sheet

Product Name
SCGC™ LLDPE

Product Type
Polyethylene for Rotational Moulding

Product Grade
M735RWP

Product Description

SCGC™ M735RWP is the powder form of M735RW, a linear low-density polyethylene (LLDPE) grade designed for rotational moulding applications. Offering high melt flow and an excellent balance of impact strength, stiffness, and processability, this grade is ideal for lawn and garden articles, decorative items, and small industrial parts.

Typical Application

- Lawn and garden articles
- Decorative items
- LED lamp covers
- Small industrial parts
- Intricate automotive articles

Product Characteristics

- High melt flow suitable for complex shape
- Superior gloss and surface finish
- Smooth inside surface
- UV8 for outdoor use
- Good rigidity and toughness

International Compliance

- Meet the requirements of U.S. Food and Drug Administration (FDA) 21 CFR Part 177.1520 Olefin polymers (c) 2.1 for food contact under conditions of use D-G (21 CFR 176.170 (c) Table 2), for all food types
- UL 94 HB (flame retardancy)

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate @ 190°C, 2.16 kg	ASTM D 1238	6.0	g/10 min
Density	ASTM D 1505	0.932	g/cm³
Melting Point	ASTM D 2117	125 (257)	°C (°F)
Crystallization Point	ASTM D 2117	113 (235)	°C (°F)
Heat Deflection Temperature @ 0.455 MPa	ASTM D 648	58 (136)	°C (°F)
Vicat Softening Temperature	ASTM D 1525	108 (226)	°C (°F)
Mechanical Properties			
Tensile Strength at Yield @ Speed 50 mm/min	ASTM D 638	17 (2500)	MPa (psi)
Tensile Strength at Break @ Speed 50 mm/min	ASTM D 638	21 (3100)	MPa (psi)
Elongation at Break @ Speed 50 mm/min	ASTM D 638	1000	%
Flexural Modulus	ASTM D 790	570 (82700)	MPa (psi)
Surface Hardness	ASTM D 2240	57	Shore D
ARM Impact Strength @ -40°C (5.5 mm rotomoulded sample)	ARM Method	25 (101)	J/mm (lb-ft)
Brittleness Temperature	ASTM D 746	< -60 (-76)	°C (°F)

Note: ● The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.

Thai Polyethylene Co., Ltd. / SCGC ICO Polymers Co., Ltd.
1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand
E-mail: rotomolding@scg.com

Published: May 2026

Processing Guidelines

Moulding cycles depend on mould materials and its wall thickness, oven temperature, and shot size. Typical oven temperatures should be set between 250 and 300 °C. The recommended PIAT for M735RWP is about 220 °C.

Points of Concerns

- It is not recommended to flame the surfaces of molded parts with an open torch due to risk of thermal degradation and premature failure.
- Inclusion of fillers or recycled materials into the resins either by compounding or dry blending is not recommended due to risk of compromised impact strength.
- Additional antioxidants, internal lubricants, or UV stabilizers into the virgin resins during the compounding process should be considered depending on the end applications.
- Not for cooking less than 10 min heating time.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Natural powder

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Co., Ltd. / SCGC ICO Polymers Co., Ltd.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services.

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Safety Data Sheet
  - Declaration of Compliance

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.