



Technical Data Sheet

Product Name

**SCGC™
LLDPE**

Product Type

Polyethylene for Rotational Moulding

Product Grade

M9001RW

Product Description

SCGC™ M9001RW is a linear-low density polyethylene (LLDPE) for rotational moulding applications. M9001RW is a natural PE resin available in a pellet form. This grade is suitable for rotational moulding of large water tanks and parts that require high stiffness.

Typical Application

- Large tanks (5,000-22,500 liters)
- Agricultural storage tanks
- Material handling containers
- Kayaks
- Manholes
- Thick wall parts (10 mm and above)
- Septic tanks
- Underground water tanks

Product Characteristics

- High stiffness and impact strength
- High thermal stability
- High UV protection (UV20) for outdoor use

International Compliance

- Meet the requirements of U.S. Food and Drug Administration (FDA) 21 CFR Part 177.1520 Olefin polymers (c) 2.1 for food contact
- Meet the requirements of AS/NZS 4020:2018 for drinking water
- Meet the requirements of AS/NZS 4766:2020 for Polyethylene storage tanks for water and chemicals
- Meet Thai Industrial Standard TIS 816-2565

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate @ 190°C, 2.16 kg	ASTM D 1238	3.2	g/10 min
Density	ASTM D 1505	0.939	g/cm ³
Melting Point	ASTM D 2117	127 (260)	°C (°F)
Crystallization Point	ASTM D 2117	113 (236)	°C (°F)
Heat Deflection Temperature @ 0.455 MPa	ASTM D 648	60 (140)	°C
Vicat Softening Temperature	ASTM D 1525	117 (243)	°C (°F)
Mechanical Properties			
Tensile Strength at Yield	ASTM D 638 @ Speed 50 mm/min	18 (2600)	MPa (psi)
Tensile Strength at Break	ASTM D 638 @ Speed 50 mm/min	29 (4200)	MPa (psi)
Elongation at Break @ Speed 50 mm/min	ASTM D 638	1300	%
Flexural Modulus	ASTM D 790	890 (129000)	MPa (psi)
Surface Hardness	ASTM D 2240	60	Shore D
ARM Impact Strength @ -40°C (5.5 mm rotomoulded sample)	ARM Method	29 (118)	J/mm (lb-ft)
Brittleness Temperature	ASTM D 746	< -60 (-76)	°C (°F)

Note: • The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.



Technical Data Sheet	Product Name SCGC™ LLDPE
	Product Grade M9001RW
Product Type Polyethylene for Rotational Moulding	

Processing Guidelines

Moulding cycles depend on mould materials and its wall thickness, oven temperature, and shot size. Typical oven temperatures should be set between 250 and 300 °C. The recommended PIAT for M9001RW is about 195 °C.

Points of Concerns

- It is not recommended to flame the surfaces of molded parts with an open torch due to risk of thermal degradation and premature failure.
- Inclusion of fillers or recycled materials into the resins either by compounding or dry blending is not recommended due to risk of compromised impact strength.
- Additional antioxidants, internal lubricants, or UV stabilizers into the virgin resins during the compounding process should be considered depending on the end applications.
- Due to a slightly off-white color, M9001RW is not recommended for finished products that require pure-white appearance.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Natural pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Co., Ltd. / SCGC ICO Polymers Co., Ltd.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services.



Technical Data Sheet

Product Name

**SCGC™
LLDPE**

Product Type

Polyethylene for Rotational Moulding

Product Grade

M9001RW

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Safety Data Sheet
 - Declaration of Compliance

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.