



Technical Data Sheet

Product Name
**SCGC™ PP:
Random copolymer**

Product Type
Polypropylene

Product Grade
P791C

Product Description

SCGC™ PP P791C is a polypropylene product which is specially designed for extrusion coating or lamination with excellent bonding strength for PP substrate, toughness, and impact strength. SCGC™ PP P791C can be used in high performance coating application for example cement bag, high load FIBC bag, and high performance laminated woven bag with BOPP etc.

Typical Application

- Intermediate Bulk Containers (FIBC), Tarpaulin
- BOPP or paper lamination with PP woven bags

Product Characteristics

- Superior bonding strength to both BOPP and PP woven
- Stable processing & less neck in
- Enhance impact strength & product flexibility
- Able to run at wide range of coating speed 80 – 250 m/min

International Compliance

- Directive 94/62/EC
- US. FDA 21 CFR 177.1520
- Regulation (EU) No. 10/2011

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate at 230 °C and 2.16 kg	ASTM D 1238	22	g/10 min
Density	ASTM D 1505	0.910	g/cm ³
Melting Point	ASTM D 2117	148	°C
VICAT Softening Temperature	ASTM D 1525	125	°C
Tensile Strength at Yield	ASTM D 638	208	kg/cm ²
Tensile Strength at Break	ASTM D 638	136	kg/cm ²
Elongation at Break	ASTM D 638	444	%
Flexural Modulus	ASTM D 790	7,885	kg/cm ²

Note: • The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.



Technical Data Sheet		Product Name SCGC™ PP: Random copolymer
Product Type Polypropylene	Product Grade P791C	

Processing Guidelines

Extrusion coating and lamination: Extruder temperature around 200 – 280 °C, Die temperature around 260 – 290 °C, Maximum coating line speed 250 m/min. However, these conditions are only guideline for actual processing conditions should be adjusted case by case because it depends on machine type, screw configuration, product design and environment.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Co., Ltd.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products;
for more information, contact your SCG Chemicals technical services.



Technical Data Sheet		Product Name SCGC™ PP: Random copolymer
Product Type Polypropylene		Product Grade P791C

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products;
for more information, contact your SCG Chemicals technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Safety Data Sheet
 - Declaration of Compliance

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.