



Technical Data Sheet

Product Name

**SCGC™
PVC: Resin**

Product Type

PVC Resin - General Grade

Product Grade

SP660

Product Description

Polyvinyl Chloride Homopolymer having medium molecular weight, is white and free-flowing resin produced by suspension polymerization process. The resin can easily blend with variety of additives to achieve desired qualities needed in many applications. Applications are ranging from general purpose to special products regarding customer satisfaction.

Typical Application

- Door, window frame, and edge bond
- Floor tile (stone-plastic composite, SPC)
- Rigid construction profile
- Pipes and conduits

Product Characteristics

- High bulk density
- Good flowability
- Good thermal stability

International Compliance

- RoHS Directive 2011/65/EU Annex II
- EU REACH Compliance (Under control EU import volume)

*The information provided is based on our knowledge and is intended as a guide. Users are responsible for testing the products for their specific application and complying with all applicable laws and regulations. The Company makes no warranties or guarantees for any use of the product in any application. It is strongly recommended to discuss any concerns with the Company's technical service team regarding activities related to the production and/or manufacturing of the product in any applications related to medical devices, cosmetics packaging, personal care packaging, food and feed packaging, drinking water, etc.

Physical Properties

Properties	Test Method	Typical Value	Unit
K-Value	ISO 1628-2	65.4	-
Apparent Bulk Density	ISO 60	0.56	g/ml
Volatile Matter	ISO 1269	< 0.3	%
Sieve Analysis: Retained on 250 microns	ASTM D1921	< 2.0	%
Sieve Analysis: Retained on 75 microns	ASTM D1921	> 90.0	%
Impurity and Foreign Matter	TPC Method	< 10	points/100 g
Residual VCM	ASTM D3749	< 1	ppm

- Note:**
- The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
 - Corresponding Polymerization Degree = 1,030



Technical Data Sheet		Product Name SCGC™ PVC: Resin
Product Type PVC Resin - General Grade	Product Grade SP660	

Processing Guidelines

PVC resin needs to be compounded with the proper additives by using standard mixing techniques. The optimal processing conditions for each converter depend on the formulation and the machine. Generally, the processing temperature is 120 to 170°C for soft products and 170 to 210°C for rigid products.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- White powder

Product Packaging

- 25 kg loose bag
- 550 kg and 1,100 kg flexy bag
- 10 MT and 20 MT tank car
- 17 MT seabulk

Storage

- Use with adequate ventilation. Avoid contact with eyes and skin. Good housekeeping measures should be used and accumulations of materials should be removed from settling areas.
- Polyvinyl Chloride can acquire a substantial static electrical charge. Handling and processing equipment should have an electrical grounding.
- Store and handle in accordance with all current regulations and standards. Container tightly closed and properly labeled. Store in a cool, dry area. Store in a well-ventilated area. Avoid heat, flames, sparks and other sources of ignition.
- Recommend to use the product within 1 year, start from manufacturing period which is referenced from lot number printed on package, to prevent any changing.
- Arrange product properly and correctly methods. For more information, please see "PVC User manual"

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products;
for more information, contact your SCG Chemicals technical services.



Technical Data Sheet		Product Name SCGC™ PVC: Resin
Product Type PVC Resin - General Grade	Product Grade SP660	

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products;
for more information, contact your SCG Chemicals technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Material Safety Data Sheet
 - PVC User Manual

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.